

PRODUCT DATA SHEET

GEOTEX® 2130

Geotex 2130, produced by Propex, is a polypropylene woven flat tape silt fence fabric that meets AASHTO M-288 Standards for silt fence usage. This engineered fabric is stabilized to resist degradation due to ultraviolet exposure. It is resistant to commonly encountered soil chemicals, mildew and insects, and is non-biodegradable. Polypropylene is stable within a pH range of 2 to 13, making it one of the most stable polymers available for geotextiles today.

Geotex 2130 conforms to the property values listed below¹. Propex performs internal Manufacturing Quality Control (MQC) tests that have been accredited by the Geosynthetic Accreditation Institute – Laboratory Accreditation Program (GAI-LAP).

PROPERTY	TEST METHOD	MARV ²	
		ENGLISH	METRIC
Mechanical			
Tensile Strength (Grab)	ASTM D-4632	124 x 124 lbs	550 x 550 N
Elongation	ASTM D-4632	15 x 20%	15 x 20%
Puncture	ASTM D-4833	65 lbs	285 N
Mullen Burst	ASTM D-3786	300 psi	2060 kPa
Trapezoidal Tear	ASTM D-4533	65 lbs	285 N
Endurance			
UV Resistance	ASTM D-4355	80%	80%
Hydraulic			
Apparent Opening Size (AOS) ³	ASTM D-4751	30 US Std. Sieve	0.600 mm
Permittivity	ASTM D-4491	0.1 sec ⁻¹	0.1 sec ⁻¹
Water Flow Rate	ASTM D-4491	8 gpm/ft ²	325 l/min/m ²
Roll Sizes⁴		2 ft x MR	0.61 m x MR
		3 ft x MR	0.91 m x MR
		3.5 ft x MR	1.07 m x MR

NOTES:

1. The property values listed above are effective 08/2006 and are subject to change without notice.
2. Values for machine (warp) and cross-machine (fill), respectively, under dry or saturated conditions. Minimum average roll values (MARV) are calculated as the typical minus two standard deviations. Statistically, it yields a 97.7% degree of confidence that any samples taken from quality assurance testing will exceed the value reported.
3. Maximum average roll value.
4. MR indicates Master Roll.



THE ADVANTAGE CREATORS.™

Propex Inc.
6025 Lee Highway, Suite 425
PO Box 22788
Chattanooga, TN 37422

PH: 423 899 0444
PH: 800 621 1273
FAX: 423 899 7619
www.geotextile.com

Geotex®, Landlok®, Pyramat®, X3®, SuperGro®, Petromat® and Petrotac® are registered trademarks of Propex Inc. THIS PUBLICATION SHOULD NOT BE CONSTRUED AS ENGINEERING ADVICE. WHILE INFORMATION CONTAINED IN THIS PUBLICATION IS ACCURATE TO THE BEST OF OUR KNOWLEDGE, PROPEX DOES NOT WARRANT ITS ACCURACY OR COMPLETENESS. THE ULTIMATE CUSTOMER AND USER OF THE PRODUCTS SHOULD ASSUME SOLE RESPONSIBILITY FOR THE FINAL DETERMINATION OF THE SUITABILITY OF THE INFORMATION AND THE PRODUCTS FOR THE CONTEMPLATED AND ACTUAL USE. THE ONLY WARRANTY MADE BY PROPEX FOR ITS PRODUCTS IS SET FORTH IN OUR PRODUCT DATA SHEETS FOR THE PRODUCT, OR SUCH OTHER WRITTEN WARRANTY AS MAY BE AGREED BY PROPEX AND INDIVIDUAL CUSTOMERS. PROPEX SPECIFICALLY DISCLAIMS ALL OTHER WARRANTIES, EXPRESS OR IMPLIED, INCLUDING WITHOUT LIMITATION, WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, OR ARISING FROM PROVISION OF SAMPLES, A COURSE OF DEALING OR USAGE OF TRADE.